

TEST REPORT NO:075395

Date:28 February 2013

BUTE FABRICS LIMITED
4 BARONE ROAD
ROTHESAY
ISLE OF BUTE
SCOTLAND
PA20 ODP

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	Yellow Woven Fabric CF731
Retailer style number	Buttercup 233 22414/01
Retailer Standard Number	Unknown
Order No./ Buyer	135399/2987
Quality/Fibre Composition	85% Pure New Wool 15% Nylon
Date Sample(s) Received:	31 January 2013

Test

Abrasion Resistance (BS EN ISO 12947-1:1999)

To End Point

Head 4 Breakdown	116,000 Rubs
Head 5 Breakdown	124,000 Rubs
Head 6 Breakdown	124,000 Rubs
Average	121,333 Rubs

Shade Change @ 3,000 Rubs Grade 4/5

Remarks

Tests as requested by the customer

Signature

M. Harrison
M. Harrison Laboratory Manager

For and on behalf of
SGS Leicester Ltd.

End of Report

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only